

AD-A143 159

EFFECT OF POLYDISPERSITY ON THE CLOUD POINT CURVES OF
POLYMER MIXTURES(U) CINCINNATI UNIV OH DEPT OF
MATERIALS SCIENCE AND METALLURGICAL R J ROE ET AL.

1/1

UNCLASSIFIED


15 JUN 84 N00014-77-C-0376

F/G 7/3

NL

										END DATA FILMED 8-84 DTIC			





MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS 1963-A

AD-A143 159

DTIC FILE COPY

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER No. 10	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Effect of Polydispersity on the Cloud Point Curves of Polymer Mixtures		5. TYPE OF REPORT & PERIOD COVERED Technical Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) R. J. Roe and L. Lu		8. CONTRACT OR GRANT NUMBER(s) ONR N00014-77-C-0376
9. PERFORMING ORGANIZATION NAME AND ADDRESS University of Cincinnati Cincinnati, Ohio 45221-0012		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR 356-655
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research 800 N. Quincy Street Arlington, VA 22217		12. REPORT DATE June 15, 1984
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		13. NUMBER OF PAGES 16
		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Distribution Unlimited. Approved for Public Release.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A method is presented for the calculation of cloud point curves of polymer-polymer mixtures when the polymers involved are polydisperse. The method is based on the Flory-Huggins free energy of mixing with a concentration-independent χ parameter. Numerical results are given for the cases where the molecular weight distributions are represented by the Schulz-Flory type. When the two polymers have similar average molecular weights and		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-LF-014-660184 07 18 016
SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

from
over
SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

polydispersities, the cloud point curves become flatter as the polydispersity increases. When the two polymers have similar average molecular weights but differ in their polydispersities, the cloud point curves become more skewed as the difference in the polydispersity increases. The results point out that, if the polydispersity effect is not properly accounted for, the value of χ deduced from experimental cloud points is liable to be in error, especially with regard to its temperature coefficient or its concentration dependence.



Accession No.	
File No.	
Index No.	
Class No.	
Sub No.	
Rev.	
Dist.	
Avail.	
Dist.	
A-1	

OFFICE OF NAVAL RESEARCH
Contract N00014-77-C-0376
Task No. NR 356-655
TECHNICAL REPORT NO. 10

Effect of Polydispersity on the Cloud Point Curves
of Polymer Mixtures

by

Ryong-Joon Roe and Learong Lu

Prepared for Publication
in Journal of Polymer Science

Department of Materials Science
and Metallurgical Engineering
University of Cincinnati

June 15, 1984

Reproduction in whole or in part is permitted for
any purpose of the United States Government

This document has been approved for public release
and sale; its distribution is unlimited

Effect of Polydispersity on the Cloud Point Curves of Polymer Mixtures

Ryong-Joon Roe and Learong Lu
Department of Materials Science and Metallurgical Engineering
University of Cincinnati, Cincinnati, OH 45221-0012

ABSTRACT

A method is presented for the calculation of cloud point curves of polymer-polymer mixtures when the polymers involved are polydisperse. The method is based on the Flory-Huggins free energy of mixing with a concentration-independent χ parameter. Numerical results are given for the cases where the molecular weight distributions are represented by the Schulz-Flory type. When the two polymers have similar average molecular weights and polydispersities, the cloud point curves become flatter as the polydispersity increases. When the two polymers have similar average molecular weights but differ in their polydispersities, the cloud point curves become more skewed as the difference in the polydispersity increases. The results point out that, if the polydispersity effect is not properly accounted for, the value of χ deduced from experimental cloud points is liable to be in error, especially with regard to its temperature coefficient or its concentration dependence.

INTRODUCTION

As is well known, the solubility between two polymers is in general severely limited because of the rather small entropic gain achieved on mixing large molecules. Since the molecular weight heterogeneity modifies only the entropic term, which is already small to begin with, it could be expected that the polydispersity influences the miscibility behavior of polymers only weakly. This is certainly true when the polymers involved are all of extremely high molecular weights. In many recent studies¹⁻³ of thermodynamics of polymer mixtures, especially of those exhibiting UCST behavior, however, the polymers involved were of relatively low molecular weights, so that a proper consideration would have to be given to the possible effect of polydispersity. With systems exhibiting LCST behavior the phase separation is brought about usually by a change in the sign of the χ parameter accompanying a temperature change. In such cases the absolute magnitude of the χ term is small and therefore the modification of the small entropic term by the polydispersity effect, even when the molecular weights are high, may appreciably affect the observed cloud point curves.

Extensive analyses have been made, by Koningsveld,⁴ Solc,⁵ and others,⁶ on the effect of polydispersity on phase separation of polymer solutions, i.e., solutions of a polydisperse polymer in a low molecular weight solvent. These analyses all start from the Flory-Huggins free energy of mixing (or its modification). In this work we likewise take the Flory-Huggins expression for the mixing of two polymers as the starting point, and investigate

numerically the expected binodal curves as a function of the polydispersity of the two polymers. As has been stressed in recent years,⁷ the mean-field approximation embodied in the Flory-Huggins expression is fairly satisfactory in describing the thermodynamics of polymer-polymer mixtures. A recent study by Joanny⁸ of the critical behavior of polymer mixtures explicitly confirms this. This is to be contrasted with the fact that for a polymer solution the Flory-Huggins formula becomes grossly inadequate near the critical point and at dilute concentrations.

Both for polymer-solvent and polymer-polymer systems the effect of polydispersity on the spinodal curve and the critical point can be deduced fairly easily. When the χ parameter is independent of molecular weights (but may be dependent on the concentration), it has been known⁹ that the spinodal curve depends only on the weight-average molecular weight and the critical point on the weight-average and z-average molecular weights. No such simple results, however, arise in the case of the binodal curve, which depends on the details of the molecular weight distribution and can therefore be deduced only numerically.

METHOD

We start the analysis with the Flory-Huggins free energy of mixing in the following form:

$$\Delta G_M/RT = \sum_p (\phi_{1p}/p) \ln \phi_{1p} + \sum_p (\phi_{2p}/p) \ln \phi_{2p} + \chi \phi_1 \phi_2 \quad (1)$$

where ϕ_{1p} is the volume fraction of the p-mer of polymer 1,

$$\phi_1 = \frac{\sum \phi_{1p}}{p}; \quad \phi_1 + \phi_2 = 1 \quad (2)$$

and χ is a function of temperature but is independent of ϕ . The chemical potential is derived from equation (1) as:

$$\Delta\mu_{1p}/RT = \ln\phi_{1p} + 1 - p(\phi_1/p_{1n} + \phi_2/p_{2n}) + \chi p(\phi_2)^2 \quad (3)$$

where p_{1n} is the number-average DP of polymer 1. When two phases coexist, the chemical potentials of each species in the phases A and B are equal: $\Delta\mu_{1p}^A = \Delta\mu_{1p}^B$, and it therefore follows that:

$$\phi_{1p}^A / \phi_{1p}^B = \exp(\sigma_{1p}); \quad \phi_{2p}^A / \phi_{2p}^B = \exp(\sigma_{2p}) \quad (4)$$

where

$$\sigma_1 = \phi_1^A/p_{1n}^A + \phi_2^A/p_{2n}^A - \phi_1^B/p_{1n}^B - \phi_2^B/p_{2n}^B - \chi[(\phi_2^A)^2 - (\phi_2^B)^2] \quad (5)$$

and

$$\sigma_2 = \phi_1^A/p_{1n}^A + \phi_2^A/p_{2n}^A - \phi_1^B/p_{1n}^B - \phi_2^B/p_{2n}^B - \chi[(\phi_1^A)^2 - (\phi_1^B)^2] \quad (6)$$

At the cloud point, at which an infinitesimal volume of phase A has just separated out, the composition of phase B is essentially the same as the composition of the whole mixture:

$$\phi_{1p}^B \rightarrow \phi_{1p} \quad (\text{cloud point}) \quad (7)$$

Eliminating χ from (5) and (6) and using the condition (7), we find:

$$(\phi_1^A + \phi_1) \sigma_{1/2} + (\phi_2^A + \phi_2) \sigma_{2/2} = (\phi_1^A/p_{1n}^A + \phi_2^A/p_{2n}^A) - (\phi_1/p_{1n} + \phi_2/p_{2n}) \quad (8)$$

If $w_1(p)$ and $w_2(p)$ are the (normalized) molecular weight

distributions (by weight) of polymer 1 and polymer 2 respectively, the quantities in equation (8) pertaining to the incipient phase A can be expressed as:

$$\phi_1^A = \phi_1 \sum_p w_1(p) \exp(\sigma_1 p) \quad (9)$$

$$\phi_1^A / p_{1n}^A = \phi_1 \sum_p (1/p) w_1(p) \exp(\sigma_1 p) \quad (10)$$

and similarly for ϕ_2^A and ϕ_2^A / p_{2n}^A . Thus, equation (8) can be regarded as an implicit equation $f(\sigma_1, \sigma_2) = 0$ for two unknowns σ_1 and σ_2 . Another implicit equation for σ_1 and σ_2 arises from the condition that:

$$\phi_1^A + \phi_2^A = 1 \quad (11)$$

in conjunction with equation (9). Thus, equations (8) and (11) constitute a set of two simultaneous equations which can be solved for σ_1 and σ_2 for given values of ϕ_1 , $w_1(p)$, and $w_2(p)$. χ can then be evaluated from either equation (5) or (6).

For numerical calculation of the cloud point curve, we assume the molecular weight distribution $w(p)$ to be given by the so-called Schulz-Flory distribution:

$$w(p) = (a^{k+1} p^k / k!) \exp(-ap) \quad (12)$$

where the parameters a and k are related to the number average DP, p_n , and the polydispersity index, $\beta = p_w / p_n$, by

$$p_n = k/a; \quad \beta = 1 + 1/k \quad (13)$$

The summations indicated by equations (9) and (10) can then be easily evaluated by integration. The numerical solution of the equations (8) and (11) for σ_1 and σ_2 is then straightforward.

All results shown below were obtained with a PDP 11/23 computer.

RESULTS AND DISCUSSION

Fig. 1 shows the cloud point curves calculated for the case where $P_{1w} = P_{2w} = 1000$ and $\beta_1 = \beta_2 = 1.0, 1.1,$ and 2.0 respectively. The three curves go through the common critical point at $\phi_1 = 0.5$. When χ is independent of composition, the spinodal curve is given by:

$$1/P_{1w}\phi_1 + 1/P_{2w}\phi_2 = 2\chi \quad (14)$$

and the critical point by:

$$1/\phi_{2c} = 1 + P_{2w}P_{1z}^{1/2}/P_{1w}P_{2z}^{1/2} \quad (15)$$

and

$$2\chi_c = (1/P_{1z}^{1/2} + 1/P_{2z}^{1/2})(P_{1z}^{1/2}/P_{1w} + P_{2z}^{1/2}/P_{2w}), \quad (16)$$

from which it can easily be shown that the three curves should share the critical point. For polymer pairs having p_{1w} (and p_{2w}) different from 1000 the curves remain the same if χ values are suitably rescaled. This can be seen from the fact that the structure of the Flory-Huggins equation remains unaltered when all the molecular lengths are reduced by a constant factor and χ , at the same time, is multiplied by the same factor.

The most interesting feature of Fig. 1 is that as the polydispersity index β is increased, the cloud point curves become flatter. In other words, at compositions away from $\phi_1 = 0.5$, phase separation occurs more readily (i.e., at a lower value of χ) as the polymers become more polydisperse. To

understand why this happens, we analyze the composition of the minority phase (or phase A) which just begins to come out as a separate phase at the cloud point. Fig. 2 shows the calculated values of ϕ_1^A vs. χ (the so-called shadow curve) for $p_{1w} = p_{2w} = 1000$ and $\beta_1 = \beta_2 = 2.0$. The cloud point and the spinodal curves are also shown there. The horizontal line ties a point on the shadow curve with a point on the cloud point curve, indicating that these two points correspond to the compositions of the coexisting phases at the given value of χ . Fig. 3 shows the weight-average p_{1w}^A of polymer 1 in phase A separated out from the principal phase of composition ϕ_1 . Thus, when a mixture containing, say, 20% of polymer 1 is brought to the condition of incipient phase separation, the minority phase that is being formed contains 68.67% of polymer 1, instead of 80% as would be expected if both polymers were monodisperse. The polymer 1 in phase A consists predominantly of higher molecular weight fractions of the original polymer so that its weight-average DP is now equal to 1853. Thus, this fractionation, in favor of the higher molecular weight end of the distribution, is responsible for the separation occurring prematurely at a value of χ smaller than otherwise.

For the polymers having the Schulz-Flory distribution considered here, the polydispersity index of the polymers separating out in the minority phase is not different from that in the principal phase. This is so, since from equations (4), (7) and (12), we have:

$$w^A(p) = (a^{k+1} p^k / k!) \exp [-(a - \phi p)] \quad (17)$$

showing that the index $\beta = 1 + 1/k$ is unaltered. The same conclusion is reached even when one of the components involved is a low molecular weight solvent. Thus, in the case of a polymer having the Schulz-Flory distribution, the width of the distribution cannot be made narrower by fractional precipitation.^{5a}

Figs. 4 and 5 show the cloud point curves calculated for the cases where $p_{1w} = p_{2w} = 1000$ but $\beta_1 \neq \beta_2$. The cloud point curves develop assymetry as the polydispersity indices of the two polymers deviate from each other. The distortion of the curve away from the symmetrical shape is in the same direction as one would have found if one had made the p_w of one of the polymers larger, instead of making its distribution broader.

One of the most practical ways of determining χ parameters between polymer pairs is to determine the cloud points experimentally and then find the best value of χ which brings the observed values in agreement with the cloud point curves calculated in accordance with the Flory-Huggins expression. In such a procedure, the effect of polydispersity is normally neglected because of computational difficulties. The present results show that unless the polymers employed have fairly narrow distributions, the χ values thus obtained could entail an appreciable error. When the two polymers are symmetrical with respect to p_w and β , the error is more likely to affect the temperature coefficient of the χ parameter, while when the two polymers differ in their polydispersity, the error is more likely to affect the concentration dependence of the χ parameter.

In the analysis of the cloud point curves of polymer-solvent systems, it was shown⁵ that a computational difficulty arises when the molecular weight distribution is a "divergent" type (for example, log-normal distribution), and also that in the vicinity of the critical point a more complicated phase relations, sometimes leading to a coexistence of three phases, could be encountered. Analogous situations are expected to arise in the case of polymer-polymer systems as well, but we have not investigated these subtleties in this work.

Acknowledgment

This work has been supported in part by the Office of Naval Research.

REFERENCES

1. D. McIntyre, N. Rounds and E. Campos-Lopez, Polym Preprints, 10, 531 (1969).
2. R. Koningsveld and L. A. Kleintjens, J. Polymer Sci., Symp. 61, 221 (1977).
3. R. J. Roe and W. C. Zin, Macromolecules, 13, 1221 (1980).
4. R. Koningsveld and A. J. Staverman, J. Polymer Sci., A-2, 6, 305, 325, 349 (1968).
5. K. Solc, (a) Coll. Czechoslov. Chem. Comm. 34, 992 (1969); (b) Macromolecules, 3, 665 (1970); (c) Macromolecules, 8, 105 (1975).
6. P. A. Irvine and J. W. Kennedy, Macromolecules, 15, 105 (1982).
7. P. G. deGennes, "Scaling Concepts in Polymer Physics", Cornell University Press, Ithaca, N.Y., 1979, Chap. IV
8. J. F. Joanny, C. R. Acad. Sc. Paris, Serie B, 286, 89 (1978).
9. W. H. Stockmayer, J. Chem. Phys., 17, 588 (1949).

Legends to Figures

- Figure 1. Cloud point curves calculated for the symmetrical cases: $P_{1W} = P_{2W} = 1000$ and $\beta_1 = \beta_2 = 1.0, 1.1$ and 2.0 as indicated.
- Figure 2. The cloud point curve (labeled ϕ_1) and the spinodal curve (broken line), calculated for the case where $P_{1W} = P_{2W} = 1000$ and $\beta_1 = \beta_2 = 2.0$. The curve labeled ϕ_1^A is the "shadow" curve giving the composition of the incipient minority phase A. The horizontal lines tie pairs of points giving the composition ϕ_1 of the principal phase and the composition ϕ_1^A of the minority phase which coexist at the cloud point.
- Figure 3. The ordinate gives the weight-average DP, p_{1W}^A , of polymer 1 in the incipient minority phase A which coexists with the principal phase of composition ϕ_1 , calculated for the case where $P_{1W} = P_{2W} = 1000$ and $\beta_1 = \beta_2 = 2.0$.
- Figure 4. Cloud point curves for $P_{1W} = P_{2W} = 1000$, $\beta_1 = 2.0$ and $\beta_2 = 1.0, 1.1$ and 2.0 respectively. As the polydispersities of the two polymers deviate more from each other, the curves become more unsymmetrical. It is as if the molecular weight of the broader polymer has become much higher, even though in fact the weight-average DP's of the two polymers are the same.
- Figure 5. Cloud point curves for $P_{1W} = P_{2W} = 1000$, $\beta_1 = 1$ and $\beta_2 = 1.0, 1.1$ and 2.0 respectively. See the caption for Figure 4.

Fig. 1




Fig. 2




Fig. 3




Fig. 4





Fig. 5



DL/413/83/01
GEN/413-2

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 N. Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Mr. Vincent Schaper DTNSRDC Code 2830 Annapolis, Maryland 21402	1
DTNSRDC Attn: Dr. G. Bosmajian Applied Chemistry Division Annapolis, Maryland 21401	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

DL/413/83/01
356A/413-2

TECHNICAL REPORT DISTRIBUTION LIST, 356A

Dr. M. Broadhurst
Bulk Properties Section
National Bureau of Standards
U.S. Department of Commerce
Washington, D.C. 20234

Naval Surface Weapons Center
Attn: Dr. J. M. Augl, Dr. B. Hartman
White Oak
Silver Spring, Maryland 20910

Dr. G. Goodman
Globe Union Incorporated
5757 North Green Bay Avenue
Milwaukee, Wisconsin 53201

Professor Hatsuo Ishida
Department of Macromolecular Science
Case-Western Reserve University
Cleveland, Ohio 44106

Mr. Robert W. Jones
Manager, Advanced Projects
Hughes Aircraft Company
P.O. Box 902
El Segundo, California 90245

Dr. David Soong
Department of Chemical Engineering
University of California
Berkeley, California

Dr. Curtis W. Frank
Department of Chemical Engineering
Stanford University
Stanford, California 94035

Picatinny Arsenal
Attn: A. M. Anzalone, Building 3401
SMUPA-FR-M-D
Dover, New Jersey 07801

Dr. E. Baer
Department of Macromolecular
Science
Case Western Reserve University
Cleveland, Ohio 44106

Dr. K. D. Pae
Department of Mechanics
and Materials Science
Rutgers University
New Brunswick, New Jersey 08903

NASA-Lewis Research Center
Attn: Dr. T. T. Serofini, MS-49-1
2100 Brookpark Road
Cleveland, Ohio 44135

Dr. Charles H. Sherman
Code TD 121
Naval Underwater Systems Center
New London, Connecticut 06320

Mr. Yoram S. Papir
Chevron Research Company
576 Standard Avenue
Richmond, California 94802-0627

Dr. R. S. Roe
Department of Materials Science
and Metallurgical Engineering
University of Cincinnati
Cincinnati, Ohio 45221

Dr. C. Giori
IIT Research Institute
10 West 35 Street
Chicago, Illinois 60616

Dr. Robert E. Cohen
Chemical Engineering Department
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

Dr. T. P. Conlon, Jr., Code 3622
Sandia Laboratories
Sandia Corporation
Albuquerque, New Mexico

Dr. J. K. Gillham
Department of Chemistry
Princeton University
Princeton, New Jersey 08540

DL/413/83/01
356A/413-2

TECHNICAL REPORT DISTRIBUTION LIST, 356A

Dr. D. R. Uhlmann
Department of Materials Science
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

Professor S. Senturia
Department of Electrical Engineering
Massachusetts Institute of Technology
Cambridge, Massachusetts 02129

Professor C. S. Paik Sung
Department of Materials Sciences and
Engineering Room 8-109
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

Dr. J. Lando
Department of Macromolecular Science
Case Western Reserve University
Cleveland, Ohio 44106

Dr. John Lundberg
School of Textile Engineering
Georgia Institute of Technology
Atlanta, Georgia 30332

Dr. R. S. Porter
Department of Polymer Science
and Engineering
University of Massachusetts
Amherst, Massachusetts 01002

Professor A. Heeger
Department of Chemistry
University of California
Santa Barbara, California 93106

Honeywell Power Sources Center
Defense Systems Division
104 Rock Road
Horsham, Pennsylvania 19044

Dr. Martin Kaufman
Code 38506
Naval Weapons Center
China Lake, California 93555

Dr. T. J. Reinhart, Jr., Chief
Nonmetallic Materials Division
Department of the Air Force
Air Force Materials Laboratory (AFSC)
Wright-Patterson AFB, Ohio 45433

Dr. J. A. Manson
Materials Research Center
Lehigh University
Bethlehem, Pennsylvania 18015

Professor Garth Wilkes
Department of Chemical Engineering
Virginia Polytechnic Institute
Blacksburg, Virginia 24061

Professor Brian Newman
Department of Mechanics and
Materials Science
Rutgers University
Piscataway, New Jersey 08854

Captain J. J. Auburn, USNR
AT&T Bell Laboratories
Room 6F-211
600 Mountain Avenue
Muray Hill, New Jersey 07974

